

SCC LE Series SuperCapacitors



New Low ESR Cylindrical Supercapacitors



The new series of cylindrical electrochemical double-layer capacitors offers excellent pulse power handling characteristics based on the combination of very high capacitance and very low ESR. Used by themselves or in conjunction with primary or secondary batteries, they provide extended back up time, longer battery life, and provide instantaneous power pulses as needed. Offers great solutions to Hold Up, Energy Harvesting, and Pulse Power Applications.

FEATURES

- Cap Values from 3.3F - 850F
- High pulse power capability
- Low ESR
- Low Leakage Current

APPLICATIONS

- Power Holdup Modules
- Energy Harvesting
- UPS/Industrial
- Robotic Power

HOW TO ORDER

SCC	W	50	B	127	S	S	B	LE	-
Series SuperCap Cylindrical	Diameter R = 8mm S = 10mm W = 22mm N = 25mm X = 30mm Y = 35mm	Case Length Two digits represent case length in mm, 1K = 105mm 1A = 115mm	Voltage Code B = 2.7V	Capacitance Code 127 = 120F 227 = 220F	Tolerance M = ±20% S = +30%/-10% P = +100%/-0%	Lead Format S = Solder Pin L = Weldable Pin R = Radial	Package B = Bulk T = Tray**	Series Code LE = Low ESR Design	Custom Code A1= 4mm Bent Leads* C1 = 2mm Bent Leads* * Inquire about availability for Radial Leads only **Inquire about availability

QUALITY INSPECTION

Parts are tested for Life Cycle, high temperature load life, temperature characteristics, vibration resistance, and humidity characteristics. See page 2 for more information.

TERMINATION

These supercapacitors are compatible with hand soldering, as well as reflow and wave soldering processes, so long as appropriate precautions are followed. See page 4 for more information.

OPERATING TEMPERATURE

-40°C to +65°C @ 2.7V
-40°C to +85°C @ 2.3V



SCC LE Series SuperCapacitors



New Low ESR Cylindrical Supercapacitors

RATINGS & PART NUMBER REFERENCE

AVX Part Number	Diameter (mm)	Length (mm)	Capacitance (F)	Capacitance Tolerance	Rated Voltage (V)	Rated Temperature (°C)	DCL Max @ 72 Hrs (µA)	ESR Max @ 1000 Hz (mΩ)	ESR Max @ DC (mΩ)	Peak Current (A)	Power Density (W/kg)	Max Energy (Wh)	Energy Density (Wh/kg)
Radial Lead													
SCCR20B335SRBLE	8	20	3.3	+30%/-10%	2.7	65*	25	45	55	3.7	589	0.0033	0.10
SCCS20B505SRBLE	10	20	5	+30%/-10%	2.7	65*	35	40	60	5.2	6943	0.0051	2.41
Solder Pin Lead													
SCCW50B127SSBLE	22	50	120	+30%/-10%	2.7	65*	300	6	8	82.7	4050	0.1215	4.50
SCCN50B187MSBLE	25	50	180	±20%	2.7	65*	470	5	8	99.6	3124	0.1823	5.21
SCCX50B227SSBLE	30	50	220	+30%/-10%	2.7	65*	620	5	6	128.0	3038	0.2228	4.64
SCCY68B407SSBLE	35	68	400	+30%/-10%	2.7	65*	1000	2.2	3	245.5	3352	0.4050	4.66
Weldable Pin Lead													
SCCY71B407PLBLE	35	71	400	+100%/-0%	2.7	65*	1300	1.3	1.8	314.0	5341	0.4050	4.45
SCCY71B407SLBLE	35	71	400	+30%/-10%	2.7	65*	1000	1.8	2.5	270.0	3845	0.4050	4.45
SCCY83B507PLBLE	35	83	500	+100%/-0%	2.7	65*	1500	1	1.6	375.0	5413	0.5063	5.01
SCCY83B607PLBLE	35	83	600	+100%/-0%	2.7	65*	1500	1	1.6	413.3	5016	0.6075	5.57
SCCY85B607SLBLE	35	85	600	+30%/-10%	2.7	65*	1500	1.6	1.8	389.4	4459	0.6075	5.57
SCCY1KB707PLBLE	35	105	700	+100%/-0%	2.7	65*	1900	0.9	1.45	469.0	4986	0.7088	5.86
SCCY1AB857PLBLE	35	115	850	+100%/-0%	2.7	65*	2200	0.8	1.3	545.1	4547	0.8606	5.82

*With Voltage Derating to 2.3V per Cell Temp can be rated to 85°C

QUALIFICATION TEST SUMMARY

Test	Test Method	Parameter	Limits
Life Cycle	Capacitors are cycled between specified voltage and half-rated voltage under constant current at +25°C for 500,000 cycles	Capacitance Change ESR Appearance	≤30% of initial value ≤200% initial value No remarkable defects
High Temperature Load Life	Temperature: 60 ± 2°C Voltage: 2.7V Test Duration: 1,000 +48/-0 hours	Capacitance Change ESR Appearance	≤30% of initial value ≤200% initial value No remarkable defects
Temperature Characteristics	Storage Duration: 1200 hours No Load Temperature: -40°C, +25°C, +65°C	Capacitance Change ESR Appearance	≤30% of initial value ≤200% initial value No remarkable defects
Vibration Resistance	Amplitude: 1.5mm Frequency: 1 ~ 55Hz Direction: X, Y, Z (Each for 2 hours)	Capacitance Change ESR Appearance	≤30% of initial value ≤200% initial value No remarkable defects
Humidity	Voltage: 2.7V RH: 95% Temperature: 40°C Test Duration: 1,000 +48/-0 Hours	Capacitance Change ESR Appearance	≤30% of initial value ≤200% initial value No remarkable defects


SCC LE Series SuperCapacitors




New Low ESR Cylindrical Supercapacitors

QUALITY AND RELIABILITY


Capacitance vs. Temperature



Leakage Current vs. Temperature



Equivalent Series Resistance vs. Temperature




SCC LE Series SuperCapacitors



New Low ESR Cylindrical Supercapacitors


MECHANICAL SPECIFICATIONS

Solder Pin Type 2-pin 120F, 220F parts




Cap (F)	D (mm)	L (mm)	P (mm)
120	22	52	8.5
220	30	52	10.5

Solder Pin Type 2-pin 180F part




D (mm)	L (mm)
25	50

Solder Pin Type 4-pin 400F part




D (mm)	L (mm)
35	68

Radial Lead Type 3.3F, 5F part




D (mm)	L (mm)	P (mm)
8	20	3.5
10	20	5.5

Weldable Pin Type 2-pin 400F, 600F parts



D (mm)	L (mm)
35	71
35	85

Radial Bent Lead Type



Style	B (mm)
A1	4
C1	2

SOLDERING RECOMMENDATIONS

When soldering supercapacitors to a PCB, the temperature & time that the body of the supercapacitor sees during soldering can have a negative effect on performance. We advise following these guidelines:

- Do not immerse the supercapacitors in solder. Only the leads should come in contact with the solder.
- Ensure that the body of the supercapacitor is never in contact with the molten solder, the PCB or other components during soldering.
- Excessive temperatures or excessive temperature cycling during soldering may cause the safety vent to burst or the case to shrink or crack, potentially damaging the PCB or other components, and significantly reduce the life of the capacitor.

HAND SOLDERING

Keep distance between the supercapacitor body and the tip of the soldering iron and the tip should never touch the body of the capacitor. Contact between supercapacitor body and soldering iron will cause extensive damage to the supercapacitor, and change its electrical properties. It is recommended that the soldering iron temperature should be less than 350°C, and contact time should be limited to less than 4 seconds. Too much exposure to terminal heat during soldering

can cause heat to transfer to the body of the supercapacitor, potentially damaging the electrical properties of the supercapacitor.

WAVE SOLDERING

Only use wave soldering on Radial type supercapacitors. The PCB should be preheated only from the bottom and for less than 60 seconds, with temperature at, or below, 100°C on the top side of the board for PCBs equal to or greater than 0.8 mm thick.

Solder Temperature (°C)	Suggested Solder Time (s)	Maximum Solder Time (s)
220	7	9
240	7	9
250	5	7
260	3	5

REFLOW SOLDERING

Infrared or conveyor over reflow techniques can be used on these supercapacitors. Do not use a traditional reflow oven without clear rated reflow temperature for supercapacitors.

SCC LE Series SuperCapacitors




New Low ESR Cylindrical Supercapacitors

TEST METHODS

IEC Capacitance Test Method


- Capacitance is measured using a Keithley 2400 or 2602 Meter
- Procedure
 - Charge Capacitor to Rated Voltage at room temperature
 - Disconnect parts from voltage to remove charging effects
 - Discharge cells with a constant current I determined by $4 * C * V_R$
 - Noting V_1 , t_1 , V_2 , t_2 and performing the calculation for C



- I – Discharge Current [mA], $4 * C * V_R$
- V_R – Rated Voltage
- V_1 – Initial Test Voltage, 80% of V_R
- V_2 – Final Test Voltage, 40% of V_R
- t_1 – Initial Test time
- t_2 – Final Test time
- $C = I * (t_2 - t_1) / (V_1 - V_2)$

DCL Measurement @ 25°C

- DCL is measured using a Multimeter with high internal impedance across a resistor
 - Charge Capacitor to Rated Voltage at room temperature for 72 Hours
 - Disconnect parts from Voltage by opening switch 1 (Stabilize for 10 Min)
 - Measure Voltage across a known Valued Resistor (1K Ohm)
 - Calculate DCL = V/R




Initial ESR Measurement @ 25°C

- Using an Agilent 4263B LCR Meter and a Kelvin connection
 - Measure at frequency of 1000 Hz
 - Measurement Voltage of 10mV

DC ESR Measurement

- Six steps capacity and ESRDC Test Method is used as illustrated in the figure right.
- Tests are carried out by charging and discharging the capacitor for two cycles at rated voltage and half rated voltage

- $C = (C_{DC1} + C_{DC2}) / 2$
- $ESR_{DC} = (ESR_{DC1} + ESR_{DC2}) / 2$
- Where: $C_{DC1} = I_2 * (t_5 - t_4) / (V_3 - V_4)$
- $C_{DC2} = I_2 * (t_{11} - t_{10}) / (V_9 - V_{10})$
- $ESR_{DC1} = (V_5 - V_4) / I_2$
- $ESR_{DC2} = (V_{11} - V_{10}) / I_2$
- $I_1 = I_2 = 75mA/F$



Maximum Operating Current

- This is the maximum current when capacitor temperature rise of the capacitor during its operation is less than 15°C

Maximum Peak Current

- This is the maximum current in less than 1 sec

Watt Density

- Watt Density = $(0.12 * V^2 / R_{DC}) / \text{mass}$

Energy Density

- Energy density = $(1/2 * CV^2) / (3600 * \text{mass})$

SCC LE Series SuperCapacitors



New Low ESR Cylindrical Supercapacitors

POLARITY / REVERSE VOLTAGE

In principal the positive and negative electrodes of the super-capacitors are symmetrical and in theory they should not have a polarity but for product consistency and for optimum performance the negative polarity is marked because the capacitors do not discharge completely when in use. It is recommended that the

polarity should be used as marked. If the polarity is reversed the circuit will not have a catastrophic failure but the circuit will see a much higher leakage current for a short duration of time and the life time of the super-capacitors will be reduced.

LIFE TIME AND TEMPERATURE PERFORMANCE


The life of a supercapacitor is impacted by a combination of operating voltage and the operating temperature according to the following equation:

$$\text{time to failure, } t \propto V^n \cdot \exp(-Q / k \cdot T) \dots\dots\dots(1)$$


where V is the voltage of operation, Q is the activation energy in electron volts (eV), k is the Boltzmann's constant in eV and T is the operating temperature in °K (where K is in degrees Kelvin). Typical values for the voltage exponent, n, is between 2.5 - 3.5, and Q is between 1.0 - 1.2 eV in the normal operating temperature range of 40° to 65°C.

The industry standard for super-capacitor end of life is when the equivalent series resistance, ESR, increases to 200% of the original value and the capacitance drops by 30%. Typically a super-capacitance shows an initial change in the ESR value and then levels off. If the capacitors are exposed to excessive temperatures the ESR will show a continuous degradation. In the extreme case, if the temperatures or voltages are substantially higher, than the rated voltage, this will lead to cell leakage or gas leakage and the product will show a faster change in the ESR which may increase to many times the original value.

Expected Lifetime at Various Voltages
SCC series 2.7V Rated



Expected Lifetime at Various Voltages
SCC series, 2.3V Rated



SCC LE Series SuperCapacitors



New Low ESR Cylindrical Supercapacitors

SAFETY RECOMMENDATIONS

Warnings

- To Avoid Short Circuit, after usage or test, Super Capacitor voltage needs to discharge to $\leq 0.1V$
- Do not Apply Overvoltage, Reverse Charge, Burn or Heat Higher than $150^{\circ}C$, explosion-proof valve may break open
- Do not Press, Damage or disassemble the Super Capacitor, housing could heat to high temperature causing Burns
- If you observe Overheating or Burning Smell from the capacitor disconnect Power immediately, and do not touch

Emergency Applications

- If Housing is Leaking:
 - Skin Contact: Use soap and water thoroughly to wash the area of the skin
 - Eye Contact: Flush with flowing water or saline, and immediately seek medical treatment
 - Ingestion: Immediately wash with water and seek medical treatment

Transportation

Not subjected to US DOT or IATA regulations
UN3499, <10Wh, Non-Hazardous Goods
International shipping description –
“Electronic Products – Capacitor”

Regulatory

- UL810a
- RoHS Compliant
- Reach Compliant / Halogen Free

Storage

- Capacitors may be stored within the operating temperature range of the capacitor
- Lower storage temperature is preferred as it extends the shelf life of the capacitor
- Do Not Store the Super Capacitors in the following Environments
 - High Temperature / High Humidity environments
> $70^{\circ}C$ / 40% RH
 - Direct Sunlight
 - In direct contact with water, salt oil or other chemicals
 - In direct contact with corrosive materials, acids, alkalis, or toxic gases
 - Dusty environment
 - In environment with shock and vibration conditions

Licensed by CAP-XX

AMERICAS

AVX Greenville, SC
Tel: 864-967-2150

EUROPE

AVX Limited, England
Tel: +44-1276-697000

AVX S.A.S., France
Tel: +33-1-69-18-46-00

AVX GmbH, Germany
Tel: +49-0811-95949-0

AVX SRL, Italy
Tel: +39-02-614-571

AVX Czech Republic
Tel: +420-57-57-57-521

AVX/ELCO UK
Tel: +44-1638-675000

ELCO Europe GmbH
Tel: +49-2741-299-0

AVX S.A., Spain
Tel: +34-91-63-97-197

AVX Benelux
Tel: +31-187-489-337

ASIA-PACIFIC

AVX/Japan
Tel: +81-740-32-1250

**AVX/Kyocera (S) Pte Ltd.,
Singapore**
Tel: +65-6286-7555

**AVX/Kyocera, Asia, Ltd.,
Hong Kong**
Tel: +852-2363-3303

**AVX/Kyocera Yuhan Hoesa,
South Korea**
Tel: +82-2785-6504

**AVX/Kyocera HK Ltd.,
Taiwan**
Tel: +886-2-2656-0258

**AVX/Kyocera (M) Sdn Bhd,
Malaysia**
Tel: +60-4228-1190

**AVX/Kyocera International
Trading Co. Ltd.,
Shanghai**
Tel: +86-21-3255 1933

**AVX/Kyocera Asia Ltd.,
Shenzen**
Tel: +86-755-3336-0615

**AVX/Kyocera International
Trading Co. Ltd.,
Beijing**
Tel: +86-10-6588-3528

**AVX/Kyocera India
Liaison Office**
Tel: +91-80-6450-0715

ASIA-KED (KYOCERA Electronic Devices)

KED Hong Kong Ltd.
Tel: +852-2305-1080/1223

**KED Hong Kong Ltd.
Shenzen**
Tel: +86-755-3398-9600

**KED Company Ltd.
Shanghai**
Tel: +86-21-3255-1833

**KED Hong Kong Ltd.
Beijing**
Tel: +86-10-5869-4655

KED Taiwan Ltd.
Tel: +886-2-2950-0268

**KED Korea Yuhan
Hoesa, South Korea**
Tel: +82-2-783-3604/6126

**KED (S) Pte Ltd.
Singapore**
Tel: +65-6509-0328

**Kyocera Corporation
Japan**
Tel: +81-75-604-3449

Contact:

